



Strength Rating (M)	Lbs-Ft/Ft	3,490	Modulus of Elasticity (E)	psi	380,000
Allowable Shear (V)	Lbs/Ft	2,130	Co-Extruded		Yes
Thickness (t)	inches	0.25	Section Depth	inches	7
Section Modulus (Z)	in ³ /ft	12.7	Section Width	inches	12
Moment of Inertia (I)	in ⁴ /ft	44.4	UV Stabilized		Yes
Ultimate Tensile Stress	psi	6,300	Standard	sheets/	40 &
Creep Limited stress	psi	4,000	Packaging	bundle	20



These New Jersey homeowners chose the EverLast 3.5 Series.



The values shown are nominal and may vary. The information found in this document is believed to be true and accurate. No warranties of any kind are made as to the suitability of ESP sheet piling for particular applications or results obtained therefrom. Consult with a professional engineer and/or contractor as to the suitability of this product for your particular application.